



ARCONVERT SpA
Sede legale e amministrativa:
Strada del Linfano, 12
38062 Arco (TN), Italy
Tel. +39 0464.584444 r.a.
Fax Comm. +39 0464.532024
Fax Amm. +39 0464.584490
Fax Acq. +39 0464.531291

arconvert.com
Cap. Soc. €4.000.000 i.v.
Codice Fiscale e Registro
Imprese n. 01077840682
Partita IVA e VAT Code IT
n. 01192310223
N. Mecc. TN 007450
N. REA TN 122101

DATA SHEET

PRODUCT:

Face Material: **PVC WHITE GLOSS 90**
Adhesive: **PF2**
Backing Paper: **KB135**

Face Material: **PVC WHITE GLOSS 90**

Description :

Application : Product designed for advertising and decorative labels. Good resistance to laceration and excellent flexibility. Good print results using silk-screen and offset with UV quick drying inks.

Technical Data	Grammage	Caliper	Brightness	Opacity	Glaze	Tensile-strength MD-CD	Elongation at break MD-CD
	g/m ²	micron	%	%	%	Kg/15 mm	%
	124	90					190-200

Adhesive: **PF2**

Description : Acrylic adhesive in water emulsion.

Application : Adhesive for plastic films. Good adhesion on apolar surfaces. High resistance to UV rays. High transparency makes this product ideal for "no-label-look" labels. Approved for indirect food contacts and corresponding to UNI-EN 71/3 "toys security" norms.

Technical Data	Tack	Cohesion (min)	Application Temperature (min)	Service Temperature (min)	Service Temperature (max)
	g/25 mm	hours	° C	° C	° C
	900	15	+ 10	-10	+ 100

Backing paper: **KB135**

Description: White paper coated and siliconised on one side.

Application: Backing paper for the continuous feed automatic printing application requiring an excellent dimensional stability and high rigidity.

Technical Data	Grammage	Caliper	Opacity	Trasparenza	Tensile-strength MC-CD	Elongation at break MD-CD
	g/m ²	micron	%	%	N/15mm	%
	135	130			110-65	

Date
16/04/2002

Report
n° NIN 165

Revision
3

Q.C. Manager
Ing. Sabrina Leoni

All the information and descriptions regarding Arconvert products are based research and are considered reliable, but do not constitute a warranty. Given the extent and constant development of fields of application for Arconvert self-adhesive products, the user must carefully check the suitability of the product for each specific application, bearing all the risks involved. No salesman, agent or representative is authorised to issue guarantees or information other than those contained in this guide which replaces previous editions and information contained herein is subject to change without notice.