



DATA SHEET

ARCONVERT SpA
 Sede legale e amministrativa:
 Strada del Linfano, 12
 38062 Arco (TN), Italy
 Tel. +39 0464.584444 r.a.
 Fax Comm. +39 0464.532024
 Fax Amm. +39 0464.584490
 Fax Acq. +39 0464.531291

arconvert.com
 Cap. Soc. €4.000.000 i.v.
 Codice Fiscale e Registro
 Imprese n. 01077840682
 Partita IVA e VAT Code IT
 n. 01192310223
 N. Mecc. TN 007450
 N. REA TN 122101

PRODUCT:

Face Material: **TRANSFER PLUS**
 Adhesive: **PX1**
 Backing Paper: **CB62**

Face Material: TRANSFER PLUS

Description: white woodfree paper
 Application: General all-purpose paper. Excellent printability with all conventional printing systems. Ideal for EDP applications and for thermal transfer printing.

Technical Data	Grammage	Caliper	Brightness	Opacity	Glaze	Tensile-strength h MD-CD	Elongation at break MD-CD
	g/m2	micron	%	%	%	Kg/15 mm	%
	73	73		93		8,2-4,1	

Adhesive: PX1

Description: Modified acrylic adhesive in water emulsion.
 Application: Special adhesive designed for the production of "all-temperature" pressure sensitive adhesives for paper labels which require a broad service temperature range from -20 °C up to +80 °C. Papers laminated with PX 1 possess a higher adhesion than competitive products, especially when applied to cold and moist polyethylene surfaces. Approved for indirect food contacts and corresponding to UNI-EN 71/3 "toys security" norms.

Technical Data	Tack	Cohesion (min)	Application Temperature (min)	Service Temperature (min)	Service Temperature (max)
	g/25 mm	hours	° C	° C	° C
	1600	2	+5	-20	+ 80

Backing paper: CB62

Description: Super calandered glassine paper, siliconised on one side.
 Colour: WHITE. There may be slight variations in tone.
 Application: Backing paper designed for automatic label generation. Ideal for photocells dispensing system.

Technical Data	Grammage	Caliper	Opacity	Trasparenza	Tensile-strength MC-CD	Elongation at break MD-CD
	g/m2	micron	%	%	N/15mm	%
	62	56		51	80-32	

Date
03/04/2013

Report
n° NIN 980

Revision
0

Q.C. Manager
Ing. Sabrina Leoni

All the information and descriptions regarding Arconvert products are based research and are considered reliable, but do not constitute a warranty. Given the extent and constant development of fields of application for Arconvert self-adhesive products, the user must carefully check the suitability of the product for each specific application, bearing all the risks involved. No salesman, agent or representative is authorised to issue guarantees or information other than those contained in this guide which replaces previous editions and information contained herein is subject to change without notice.