



DATA SHEET

ARCONVERT SpA
 Sede legale e amministrativa:
 Strada del Linfano, 12
 38062 Arco (TN), Italy
 Tel. +39 0464.584444 r.a.
 Fax Comm. +39 0464.532024
 Fax Amm. +39 0464.584490
 Fax Acq. +39 0464.531291

arconvert.com
 Cap. Soc. €4.000.000 i.v.
 Codice Fiscale e Registro
 Imprese n. 01077840682
 Partita IVA e VAT Code IT
 n. 01192310223
 N. Mecc. TN 007450
 N. REA TN 122101

PRODUCT:

Face Material: **COATED MC**
 Adhesive: **RE31**
 Backing Paper: **CB62**

Face Material: **COATED MC**

Description:
 Application: Machine coated paper for high quality labels.
 Ideal for multicolour prints requiring exceptional contrast and great detail.

Technical Data	Grammage	Caliper	Brightness	Opacity	Glaze	Tensile-strength h MD-CD	Elongation at break MD-CD
	g/m2	micron	%	%	%	Kg/15 mm	%
	80	65	95	88	65	5,4-3,7	

Adhesive: **RE31**

Description: Acrylic adhesive in water emulsion.
 Application: General adhesive for paper labels. Good adhesion and removability on most surfaces.
 Degree of removability depends on surface and method of application (testing recommended prior to use). Approved for indirect food contacts and corresponding to UNI-EN 71/3 "toys security" norms.

Technical Data	Tack	Cohesion (min)	Application Temperature (min)	Service Temperature (min)	Service Temperature (max)
	g/25 mm	hours	° C	° C	° C
	300	0,5	+ 5	-10	+ 80

Backing paper: **CB62**

Description: Super calandered glassine paper, siliconised on one side.
 Colour: WHITE.
 Application: Backing paper designed for automatic label generation. Ideal for photocells dispensing system.

Technical Data	Grammage	Caliper	Opacity	Trasparence	Tensile-strength MC-CD	Elongation at break MD-CD
	g/m2	micron	%	%	N/15mm	%
	62	56		51	80-32	

Date
22/03/2002

Report
n° NIN 396

Revision
1

Q.C. Manager
Ing. Sabrina Leoni

All the information and descriptions regarding Arconvert products are based research and are considered reliable, but do not constitute a warranty.
 Given the extent and constant development of fields of application for Arconvert self-adhesive products, the user must carefully check the suitability of the product for each specific application, bearing all the risks involved. No salesman, agent or representative is authorised to issue guarantees or information other than those contained in this guide which replaces previous editions and information contained herein is subject to change without notice.