



# CB coated back

Selbstdurchschreibepapier rückseitig gestrichen  
Carbonless paper coated on the back  
Papal autocopiativo dorso recubierto

Merkmal Property Propiedad	Prüfnorm Standard Norma	Einheit Unit Unidad	Wert Value Valor						Toleranz Tolerance Tolerancia
			56	60	70	80	90	95	
<b>CB</b>			56	60	70	80	90	95	
Flächengewicht Substance Gramaje	ISO 536	g/m <sup>2</sup> gsm	56	60	70	80	90	95	± 4 %
Dicke Caliper Calibre	ISO 534	µm	74	78	88	98	113	117	± 5
Glätte Oberseite Smoothness top side Lisura anverso	ISO 5627	Bekk s	35	35	35	35	35	35	± 20
Weißer R457 Brightness R457 Blancura R457	ISO 2470	%	98	105	105	105	105	105	± 3
Opazität Opacity Opacidad	ISO 2471	%	81	81	83	86	88	88	± 3
Reißlänge längs Breaking length md Longitud de rotura	ISO 1924-1	m	6.500						± 1.500
Feuchte absolut Absolute humidity Humedad absoluta		%	5,8						± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso