



CF coated front

Selbstdurchschreibepapier vorderseitig gestrichen
Carbonless paper coated on the front
Papel autocopiativo cara recubierta

Merkmal Property Propiedad	Prüfnorm Standard Norma	Einheit Unit Unidad	Wert Value Valor					Toleranz Tolerance Tolerancia
			57	80	90	130	173	
CF			57	80	90	130	173	
Flächengewicht Substance Gramaje	ISO 536	g/m ² gsm	57	80	90	130	173	± 4 %
Dicke Caliper Calibre	ISO 534	µm	70	90	105	140	200	± 5
Glätte Oberseite Smoothness top side Lisura anverso	ISO 5627	s	50	40	40	40	40	± 20
Weiß R457 Brightness R457 Blancura R457	ISO 2470	%	93	93	95	95	95	± 3 %
Reißlänge längs Breaking length md Longitud de rotura	ISO 1924-1	m	6.500					± 1.500
Feuchte absolut Absolute humidity Humedad absoluta		%	5,8					± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso

