



CFB coated front and back

Selbstdurchschreibepapier beidseitig gestrichen
 Carbonless paper coated on both sides
 Papel autocopiativo ambas caras recubiertas

Merkmal Property Propiedad	Prüfnorm Standard Norma	Einheit Unit Unidad	Wert Value Valor		Toleranz Tolerance Tolerancia
CFB			53	60	
Flächengewicht Substance Gramaje	ISO 536	g/m ² gsm	53	60	± 4 %
Dicke Caliper Calibre	ISO 534	µm	70	80	± 5
Glätte Oberseite Smoothness top side Lisura anverso	ISO 5627	s	45	45	± 20
Weiß R457 Brightness R457 Blancura R457	ISO 2470	%	92	92	± 3
Reißlänge längs Breaking length md Longitud de rotura	ISO 1924-1	m	6.500	6.500	± 1.500
Feuchte absolut Absolute humidity Humedad absoluta		%	5,8	5,8	± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso



Koehler
 PAPER GROUP

Papierfabrik August Koehler AG

Hauptstraße 2 | D-77704 Oberkirch | Phone +49 7802 81-0 | Fax +49 7802 81-4330 | www.koehlerpaper.com